



昆胜高分子材料（福建）有限公司  
KUNSUN POLYMER MATERIAL (FUJIAN) CO., LTD.  
TEL: +86-595-87250688  
泉州市惠安县辋川镇石化轻工小区  
Petrochemical light industry community,  
Wangchuan Town, Hui'an County, Quanzhou City, China

## Thermoplastic Polyurethane 热塑性聚氨酯

## Technical DataSheet 技术数据表

<b>ProductName</b> 产品名称	<b>B-764DL</b>
----------------------------	----------------

### Polyester TPU-B-700 Series/ 聚酯型TPU- B-700系列

Used for injection molding  
可用于注塑  
Excellent physical properties、good transparency  
物性优、透明性佳

### Applications 应用

Typical application : auto parts、machinery accessories、shoes materials etc  
典型用途：汽配、机械配件、鞋材等产品

Physical Properties 物理特性	Test Standard 测试标准	Unit 单位	Typical Value* 平均值
Density 密度	ASTM D792	g/cm <sup>3</sup>	1.23±0.02
Shore Hardness 肖氏硬度	ASTM D2240	Shore A Shore D	64D±2 D
Tensile Strength 拉伸强度	ASTM D412	Kgf/cm <sup>2</sup>	400
Elongation at Break 最大伸长	ASTM D412	%	320
100% Tensile Strength 拉伸强度@100%伸长	ASTM D412	Kgf/cm <sup>2</sup>	180
300% Tensile Strength 拉伸强度@300%伸长	ASTM D412	Kgf/cm <sup>2</sup>	250
Tear Strength 撕裂强度	ASTM D624	Kgf/cm	210

### Molding Conditions 成型条件

Drying 干燥	Drying Temperature 干燥温度	100°C
	Drying Time 干燥时间	2-4hrs
Processing 成型	Processing Temperature 建议成型温度	195-215°C
	Processing Mold 建议成型方式	Injection Molding 注塑成型

\* Typical values, should not equal to the true values, different processing and test conditions will result in the difference values, please confirm all results by own tests.  
平均值, 不能等同于真实值, 不同的加工过程和测试条件将会导致不同的结果, 请亲自测试以进行确认.

Note: Additional information (Storage, Drying, processing, Coloring, Post Treatment, Recycling, etc.), please contact our sales representative or technical service representative.  
存贮, 干燥, 加工, 着色, 后处理, 再生等更详细的信息请联系我们的销售代表和技术服务代表.